



MANUFACTURES AND DEALERS OF SPECIALITY CHEMICALS & AUXILIARIES

SURVEY NO 38, PLOT NO-3, NEAR SHIVRAM DYEING AND PRINTING MILL, OPP JC ENGINEERING, KADIWALA STREET, KHATODARA SURAT-395002 MOBILE NO 9825113647

EMAIL- Info@harshchemicals.com

WEBSITEwww.harshchemicals.com

Harshol-FBOL

Powerful wetting and desizing agent

Harshol-FBOL is a very powerful concentrated APEO Free wetting agent with detergencyand emusifying action useful for scouring, It works as a powerful desizing agent..

Specifications:

Composition: Di-Alkyle Aliphatic Alcohol Ethoxylate

Appearance: Clear colourless viscous liquid

Nature: Anionic/Non-ionic

pH: Neutral

Solubility: Soluble in water in all proportions

Compatibility: Compatible with anionic, non-ionic and cationic

Biodegradability: Good

Advantages:

- Powerful wetting and desizing agent cum detergent with strong emulsifying power.
- It ensures removal of water soluble impurities from natural, synthetic and blended fabtics.
- it is biodegradable

Application:

During all kinds od desizing except starch and bleaching operations 0.5gm/l to 2gm/l Harshol FBOL is recommended.

For scouring cotton

1-2-gm/L of Harshol-FBOL along with 2-3gm/L of soda ash at 80° Cto 90° C for 30-45 minutes is recommended.

For Wool and Wooll blends.

0.5-1gm/L of Harshol-FBOL is recommended.ph of 8-9with liquor ammonia at 70° C- 80° C for 30-45 minutes hot rinse is recommended.

For scouring synthetic and blends

0.5-1gm/L of Harshol-FBOL is recommended with required alkali.

Note:

The information and recommendation presented hereby complied with utmost care. But they cannot be extended to cover every possible case. They are intended only to serve as non-biding guidelines and may not be adapted to prevailing conditions.

Precautions:

- Keep the container closed while not in use.
- keep container in cool shade.
- Do not expose the material to direct sun light.
- Follow routine safety precautions and exercise good housekeeping.

Disclaimer:

The product incorporated and sold is without warranty expressed or implied. including warranty of merchantability and fitness of use of this material and condition that purchaser shall make their own tests to determine the suitability and the quality of the product for their particular purpose. The user assumes all risks of use and handling, whether or not in accordance with any statement of the supplier. Supplier's liability if any, for any action arising out of the material being supplied shall be limited to only replacement of material.